

Product Name:

Anycubic PLA Silk

Anycubic PLA Silk is a durable and reflective aesthetic filament that creates models with a silky luster. The luster can be fine-tuned by adjusting the printer's temperature settings.

Physical Properties

Property	Testing Method	Unit	Typical Value
Density/ (g/cm ³)	ISO 1183,at 23°C	g/cm ³	1.22
Melt Index/ (g/10min)	ISO 1133	g/10min	9±1
Moisture Content	ISO 787-2	%	0.28

Mechanical Properties

Property	Testing Method	Unit	Typical Value
Tensile Strength / MPa (X-Y)	ISO 527	MPa	37±4
Tensile Strength / MPa (Z)			12±4
Young's Modulus / MPa (X-Y)	ISO 527	MPa	2000±200
Young's Modulus / MPa (Z)			/
Elongation at Break / % (X-Y)	ISO 527	%	28±5
Elongation at Break / % (Z)			/
Bending Strength / MPa (X-Y)	ISO 178	MPa	66±4
Bending Strength / MPa (Z)			/
Bending Modulus / MPa (X-Y)	ISO 178	MPa	2400±160
Bending Modulus / MPa (Z)			/
Izod Impact Strength (kJ/m ²) (X-Y)	ISO 179	kJ/m ²	20±2
Izod Impact Strength (kJ/m ²) (Z)			/

*All data are based on printed test samples. '(X-Y)' and '(Z)' indicate different testing orientations (refer to the direction schematic).

Thermal Performance


Property	Testing Method	Unit	Typical Value
Glass Transition Temperature	ISO 11357-1, 10°C/min	°C	55.6
Melting Temperature	ISO 11357-1, 10°C/min	°C	164
Crystallization Temperature	ISO 11357-1, 10°C/min	°C	102
Vicat Softening Temperature (VST)	ISO 306, 10N	°C	54
Heat Deflection Temperature (HDT)	ISO 75-2, 1.8 MPa	°C	/
Heat Deflection Temperature (HDT)	ISO 75-2, 0.45MPa	°C	53

Recommended Printing Parameters


*Based on a 0.4mm nozzle, printing conditions may vary with different nozzle diameters

Parameter	Recommended Value
Nozzle Temperature	210-240
Bed Temperature	55-65
Dry Environment	55-65°C , 6-8h
Printing Speed	50-250
Extrusion Multiplier	0.95
Max Volumetric Flow Rate	12
Fan Speed	100%
Cooling Time	8
Minimum printing Speed	20
Raft Separation Distance	0.8
Retraction Speed	40


TENSILE TESTING SPECIMEN



IMPACT TESTING SPECIMEN



IMPACT TESTING SPECIMEN



Disclaimer:

The values shown in this chart are for comparison purposes only and are not appropriate for design specifications or quality assurance. Variations may arise due to printing conditions. The end-use performance of printed parts depends on materials, design, environmental conditions, and printing conditions. Please note that product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and proper disposal or recycling practices for Anycubic materials in their intended applications. Anycubic makes no warranties of any kind regarding the suitability of these materials for any specific use or application unless explicitly stated otherwise. Anycubic shall not be held liable for any damage, injury, or loss that results from the use of Anycubic materials in any application.