

THE FILAMENT PLA Matte

MATERIAL PROPERTIES

Physical		
Specific Gravity	1.29 g/cm3	D 792
Mechanical Properties		
Tensile Strength at Yield	37 MPa	D 638
Elongation at break	>9 %	D 638
Flexural Modulus	2.2 Gpa	D 790
Izod Notched	51,2 J/m	D 256
Thermal Properties		
Heat Deflection Temperature	60°C	D 648

GUIDELINE FOR PRINT SETTINGS\*

Nozzle temperature	195-220°C
Nozzle temperature (High Speed)	
Bed temperature	40-50°C
Closed chamber for printing	not necessary
Dry box recommended	No
Ruby or hardened nozzle recommended	No
Adhesive	not necessary (if you need increased adhesion or prevent warping: glue stick, Dimafix, 3DLac, Magigoo)
Cooling	Up to 100%
Surface finish	matte
Features	matte surface, biodegradable, user friendly, best choice for everyday use

\* settings are based on a 0,4 mm nozzle.  
\*\* depending on the geometrical complexity

STORAGE AND SHELF LIFE

Filament should be stored in a dry room at room temperature. Recommended storage temperature is ca. 18-25°C (64.4 -77.0°F). Keep out of moisture, sunlight and direct heat. When stored properly, product has a shelf life of 24 months.

SUPPORT

If you have any questions or experience any issues, please do not hesitate to contact us at [support@spectrumfilaments.com](mailto:support@spectrumfilaments.com)

**Disclaimer**  
The product and technical data provided in this datasheet is correct to the best of Spectrum Group Sp. z o.o. knowledge and are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary according to printing conditions, model complexity, environmental conditions, etc. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications. Spectrum Group Sp. z o.o. shall not be made liable for any damage, injury or loss induced from the use of Spectrum Group Sp. z o.o. materials in any particular application.