# Technical Data







#### **FEATURES**

Photocentric's range of flexible DLP UV photopolymers are ideal for making objects where you want a little flexibility, but still a hard object. Thin objects will compress and deflect enough to bend and return.

They exhibit very low tensile shear properties and high elongation, objects can be bent and compressed with some force. DLP UV Flexible provides excellent imaging in your desktop laser printer.

You will experience the benefits of fast exposure times and a wide exposure latitude, allowing you to hold the finest details your machine can provide. The solid material is tough, durable and long lasting provided it is stored in dry conditions away from strong UV light.

# PROCESSING INSTRUCTIONS

Follow the procedures laid out in your 3D DLP printer user manual. Polymer should be poured into the tray away from direct sunlight. Polymer can be reused but should be poured through a filter to remove solid I umps. Keep hood on a tall times. Liquid polymer is soluble in water and soap. After making cleaned objects surface tack can be removed by leaving under water in UV for 20 minutes or longer. If any surface tack persists you can remove it by wiping the part with IPA.



### **DATA**

**Viscosity** 200 cPs (At 25°C Brookfield spindle 3)

Hardness 80 Shore A

(After post exposure)

**Tensile strength** 4.9 MPa

ASTM D638 (After post exposure)

**Tensile strength** 1.5 MPa ASTM D638 (Before post exposure)

Elongation at break 75%

ASTM D638

Volumetric Shrinkage 5.7%

 Storage
 10<t>50°C

 Density
 1.18 g/cm³

## **AVAILABLE COLOURS**

Black, Clear, White

Available in 1kg bottles with non-drip cap.