



3D JAKE

Technical Data Sheet

Product name: **3DJAKE High-Temperature Resin**

Version: 1.0

Date: 02.09.2024

Physical properties

Description	Typical value	Test method
Density	1,18 g/cm ³	-
Young's modulus (Pull)	5500 MPa	ISO 527
Elongation at break	3%	ISO 527
Tensile strength	92 MPa	ISO 527
Charpy impact test	11 KJ/m ²	-
HDT B	180 °C	-

Printing parameters:

Specimens printed on an Phrozen Sonic Mighty 8K at 23°C and 50% humidity, 0,05 mm layer height, 2,2 seconds exposure time per layer.

Post-curing parameters:

30min with 200W 405nm UV LED. Conditioned 72h at 23 °C and 50% humidity.