

Technical Data Sheet

(Printed, non-injection molded)

Product name: **3DJAKE ecoPLA Sparkling**

Version: 1.0

Date: 01.01.2024

Dimensions

Size	Ø tolerance	Roundness
1,75 mm	± 0,05 mm	≥ 95%

Physical properties

Description	Typical value	Test method
Specific gravity	1,227 g/cc	ISO 1183
MFR 210 °C/2,16kg	3,12 g/10 min	ASTM-D-1238
Tensile strength at Yield	50,80 MPa	ISO 527
Strain at yield	9,225%	ISO 527
Strain at break	11,734%	ISO 527
E-Modulus	475,737 MPa	ISO 527
Impact strength	2,764kJ/ m ²	ISO 179

Thermal properties

Description	Typical value	Test method
Printing temperature	210 – 230 °C	-

Packaging:

All spools are sealed and packed with silica gel to avoid humidity.

Additional info:

Due to its low tendency to warp 3DJAKE ecoPLA Sparkling can also be printed without a heated bed.

If you have a heated bed the recommended temperature is ± 35-60°C.

PLA can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.