

ePLA-SS

Technical Data Sheet

Through the balance adjustment of the melt index and flow temperature, the ePLA-SS can flow smoothly in the molten state, and can be cooled faster during printing and molding. With this method, the smooth flowing without plug and fast cooling without deformation can be obtained during high-speed printing; Compared with ordinary materials, the printing speed is faster, the surface quality is higher, and the detail performance is better; Good adaptability. Through the optimization of materials, the dependence of fast printing on the cooling power of the printer is reduced, and the printability is excellent; It can be used for early conceptual model and rapid prototyping.

Material Status	Mass Production
Characteristics	<ul style="list-style-type: none"> • High speed printing • Smooth printed surface • Easy to print
Applications	<ul style="list-style-type: none"> • Cultural Creativity • Prototyping
Form	<ul style="list-style-type: none"> • Filament
Processing method	<ul style="list-style-type: none"> • 3D Print, FDM Print

	testing method	Typical value
Physical Properties		
Density	GB/T 1033	1.24 g/cm ³
Melt Flow Index	GB/T 3682	3.5-4.5 (190°C/2.16kg)
Mechanical Properties		
Tensile Strength	GB/T 1040	20-30 MPa
Elongation at Break	GB/T 1040	5-10 %
Flexural Strength	GB/T 9341	101.2 MPa
Flexural Modulus	GB/T 9341	3111.8 MPa
IZOD Impact Strength	GB/T 1843	3.05 kJ/m ²
Thermal Properties		
Heat distortion Temperature	GB/T 1634	50-60°C (0.45Mpa)
Continuous Service Temperature	IEC 60216	N/A
Maximum (short term) Use Temperature		N/A
Electrical Properties		
Insulation Resistance	DIN IEC 60167	N/A
Surface Resistance	DIN IEC 60093	N/A

Wuhan University Building A403-I,A901,No.6 Yuexing 2 Road,Nanshan District,Shenzhen,Guangdong

China

Tel +86 755 86581960

fax +86 755 26031982

Email: bright@brightcn.net

www.esun3d.com

Recommended printing parameters

Extruder Temperature	210 - 230°C
Build Platform Temperature	45-60°C
Fan Speed	100%
Printing Speed	40-300mm/s

Based on Bambu P1S 0.4 mm nozzle and Orcaslicer1.7.0 Beta. Printing conditions may vary with different

nozzle diameters Drying Recommendations

N/A


Precautions:

When slicing, it is best to turn on the Z seam alignment and starting point alignment functions, turn off the Z-axis lift and exit, avoid passing through the shell when idling, optimize the slicing printing path, and appropriately reduce the printing speed to achieve the best printing effect.


Mechanical Properties



Tensile testing specimen GB/T 1040



Flexural testing specimen GB/T 9341



Impact testing specimen GB/T 1043

The physical properties, mechanical properties, thermal properties, and electrical properties of the filament are obtained based on the injection molding spline test.

Print test condition:

Extruder Temperature	220°C
Build Platform Temperature	55°C
Outline/Perimeter Shells	2
Top/Bottom Layers	3
Infill Percentage	100%
Fan speed	100%
Maximum volumetric flow rate	4mm ³ /s

Based on Bambu P1S 0.4 mm nozzle and Orcaslicer1.7.0 Beta.

Notice

All information supplied by or on behalf of eSUN in relation to this product, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but the product is sold "as is". eSUN assumes no liability and makes no representations or warranties, express or implied, of merchantability, fitness for a particular purpose, or of any other nature with respect to information or the product to which information refers and nothing herein waives any of the seller's conditions of sale.

Wuhan University Building A403-I,A901,No.6 Yuexing 2 Road,Nanshan District,Shenzhen,Guangdong

China

Tel +86 755 86581960

fax +86 755 26031982

Email: bright@brightcn.net

www.esun3d.com