

ePLA-GF

Technical Data Sheet

PLA-GF is a printing consumable developed on the basis of PLA, in which 15-20% glass fiber is added to greatly enhance the rigidity and impact resistance of ordinary PLA. Bending modulus up to 4400MPa, high rigidity is not easy to distort; High impact resistance and good printability of PLA; Suitable for prototypes of mechanical parts that require rigidity and impact resistance; The wear resistance makes it suitable for printing gears and can be used as temporary functional parts

Material Status	Mass Production	
Characteristics	<ul style="list-style-type: none"> • High impact resistance • High rigidity 	<ul style="list-style-type: none"> • High wear resistance • Excellent printability
Applications	<ul style="list-style-type: none"> • Mechanical component • Automobile manufacturing 	<ul style="list-style-type: none"> • electronic engineering
Form	<ul style="list-style-type: none"> • Filament 	
Processing method	<ul style="list-style-type: none"> • 3D Print, FDM Print 	

	testing method	Typical value	
Physical Properties			
Density	GB/T 1033	1.31	g/cm ³
Melt Flow Index	GB/T 3682	6.36	(190°C/2.16kg)
Mechanical Properties			
Tensile Strength	GB/T 1040	59.27	MPa
Elongation at Break	GB/T 1040	7.99	%
Flexural Strength	GB/T 9341	85.01	MPa
Flexural Modulus	GB/T 9341	4414.89	MPa
IZOD Impact Strength	GB/T 1843	10.16	kJ/m ²
Thermal Properties			
Heat distortion Temperature	GB/T 1634	56	°C
Continuous Service Temperature	IEC 60216	N/A	
Maximum (short term) Use Temperature		N/A	
Electrical Properties			
Insulation Resistance	DIN IEC 60167	N/A	
Surface Resistance	DIN IEC 60093	N/A	

Wuhan University Building A403-I,A901, No.6 Yuexing 2 Road, Nanshan District, Shenzhen, Guangdong

China

Tel +86 755 86581960

fax +86 755 26031982

Email: bright@brightcn.net

www.esun3d.net

Recommended printing parameters

Extruder Temperature	190- 230°C
Build Platform Temperature	45-60°C
Fan Speed	100%
Printing Speed	40 - 100mm/s

Based on 0.4 mm nozzle and Simplify 3D v.4.1.2. Printing conditions may vary with different nozzle diameters

Drying Recommendations

N/A

Precautions:

Turn on the Z seam alignment . Turn off the Z-axis lifting with drawing.
Slower the printing speed.


Mechanical Properties



Tensile testing specimen GB/T 1040



Flexural testing specimen GB/T 9341



Impact testing specimen GB/T 1043

The physical properties, mechanical properties, thermal properties, and electrical properties of the line are obtained based on the injection molding spline test.

Print test condition:

Extruder Temperature	190-230°C
Build Platform Temperature	55°C
Outline/Perimeter Shells	4
Top/Bottom Layers	4
Infill Percentage	20%
Fan speed	100%
Printing speed	60mm/s

Based on 0.4 mm nozzle and Simplify 3D v.4.1.2.

Notice

All information supplied by or on behalf of eSUN in relation to this product, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but the product is sold "as is". eSUN assumes no liability and makes no representations or warranties, express or implied, of merchantability, fitness for a particular purpose, or of any other nature with respect to information or the product to which information refers and nothing herein waives any of the seller's conditions of sale.