

TPU-HS

Technical Data Sheet

It has good flexibility with a hardness of 95A, easy to print, and can quickly print large, complex and accurate prototypes of elastomer parts; excellent elasticity, printed products are not easy to deform; good flexibility, high tear resistance and wear resistance and cut resistance, sturdiness and durability; high hardness and good resilience, can be used for insoles and other applications.

Material Status	Mass Production			
Characteristics	<ul style="list-style-type: none"> • Flexible and soft • Sturdy and durable • High flexibility • High toughness • High impact resistance 			
Applications	<ul style="list-style-type: none"> • Shoe material • Machinery 	<ul style="list-style-type: none"> • Automobile • Electronic appliances 	<ul style="list-style-type: none"> • Conveying pipeline • Sporting products 	<ul style="list-style-type: none"> • Medical prosthesis
Form	<ul style="list-style-type: none"> • Filament 			
Processing method	<ul style="list-style-type: none"> • 3D Print, FDM Print 			

	Testing method	Typical value	
Physical Properties			
Density	GB/T 1033	1.21	g/cm³
Melt Flow Index	GB/T 3682	1.2	(190℃/2.16kg)
Mechanical Properties			
Tensile Strength	GB/T 1040	35	MPa
Elongation at Break	GB/T 1040	≥800	%
Flexural Strength	GB/T 9341	N/A	
Flexural Modulus	GB/T 9341	N/A	
IZOD Impact Strength	GB/T 1843	N/A	
Thermal Properties			
Heat distortion Temperature	GB/T 1634	N/A	
Continuous Service Temperature	IEC 60216	N/A	
Maximum (short term) Use Temperature		N/A	
Electrical Properties			
Insulation Resistance	DIN IEC 60167	N/A	
Surface Resistance	DIN IEC 60093	N/A	

Wuhan University Building A403-I,A901,No.6 Yuexing 2 Road,Nanshan District,Shenzhen,Guangdong
China

Tel +86 755 86581960
fax +86 755 26031982
Email: bright@brightn.net
www.esun3d.net

Recommended printing parameters

Extruder Temperature	220 - 250°C
Build Platform Temperature	45-60°C
Fan Speed	100%
Printing Speed	20 - 50mm/s

Based on 0.4 mm nozzle and Simplify 3D v.4.1.2. Printing conditions may vary with different nozzle diameters


Drying Recommendations

N/A


Notes

1. It is recommended to dry the printing (55°C/ >4H) to achieve the best printing effect. It is recommended to use it with eBOX cartridges when printing.
2. It is recommended to use a short-range two-wheel reduction extruder designed for flexibility, TPU-HS materials are usually difficult to print on a remote extrusion machine. The remote extruder can try to print at a slower speed at 20mm/s or even slower.
3. The nozzle may have impurities after printing for a long time. It is recommended to use it with the cleaning filament. If necessary, replace the nozzle and throat with a new one.


Mechanical Properties



Tensile testing specimen GB/T 1040



Flexural testing specimen GB/T 9341



Impact testing specimen GB/T 1043

The physical properties, mechanical properties, thermal properties, and electrical properties of the filament are obtained based on the injection molding spline test.

Print test condition :

Extruder Temperature	210-250°C
Build Platform Temperature	60°C
Outline/Perimeter Shells	4
Top/Bottom Layers	4
Infill Percentage	20%
Fan speed	100%
Printing speed	40mm/s

Based on 0.4 mm nozzle and Simplify 3D v.4.1.2.

Notice

All information supplied by or on behalf of eSUN in relation to this product, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but the product is sold "as is". eSUN assumes no liability and makes no representations or warranties, express or implied, of merchantability, fitness for a particular purpose, or of any other nature with respect to information or the product to which information refers and nothing herein waives any of the seller's conditions of sale.