



TECHNICAL DATA SHEET

FLEX MEDIUM

1. DESCRIPTION

TPU FLEX Medium has been specially developed for the FDM/FFF process. With an extensibility of up to 470%, high material quality, high chemical resistance and a heat distortion resistance of up to 115°C, the material is suitable for numerous industrial applications. The raw material is compliant with REACH and RoHS standards.

2. FEATURES

- Very impact and breakage resistant
- Halogen-free
- Free of silicone, plasticisers and oils
- Shore hardness A98
- UV-resistant
- Extreme layer adhesion

3. PROPERTIES

TEST	METHOD	UNIT	VALUE	PRINT SETTINGS
Tensile modulus (E-Modulus)	ISO 527-2/5A/500	MPa	40	Nozzle 230-250°C
Ultimate elongation	ISO 527-2/5A/500	%	475	Heatbed 50-90°C
Stress at break	ISO 527-2/5A/500	MPa	- (50%)	Adhesive not required
	ISO 527-2/5A/500	MPa	17 (100%)	Speed 20-100mm/s
	ISO 527-2/5A/500	MPa	30 (300%)	Cooling 0-30%
VICAT A (VST)	ISO 306	°C	110*	Enclosed Space no
Melting temperature	ISO 3146-C	°C	190-220	Hardened Nozzle no
Density	ISO 2781	g/cm ³	1.19	Max. Volumetric Speed 3,2 mm ³ /s
Abrasion resistance	ISO 4649-A	mm ³	25	
Shore hardness	ISO 868	Shore	98A	
Tear strength	ISO 34-1B	kN/m	170	
Glass transition temperature		°C	-30	
Compressive strength	DIN 53452	MPa	40	
Permeability AIR	DIN 53380	25°/60°C	450/-	
Permeability N2	DIN 53380	25°/60°C	330/1800	
Permeability O2	DIN 53380	25°/60°C	840/4500	
Permeability CO2	DIN 53380	25°/60°C	6500/19000	
Permeability N2O	DIN 53380	25°/60°C	12400/-	
Poisson-ratio	acc. to Hencky		0.47	

Recommended settings for printers with a 0.4mm Nozzle.
Max. 50% layerheight. Optimal print settings may vary between different printers and also depend on environmental factors.

*Temperature resistance tested at a minimum wall thickness of 4 mm.

4. CERTIFICATIONS & ADDITIONAL INFORMATION



Certifications depend on colors in final product. More info in the additional information sheet.

5. STORAGE AND SHELF LIFE

Store in a dry room at room temperature (18-27°C / 65-80°F). Keep out of direct heat and sunlight.

When stored correctly, this material has a shelf life of 2 years.

Additional info in our regulatory, additional information and chemical resistance data sheets.