

TECHNICAL DATA SHEET

Tough PLA

Date of issue: 7-6-2022

Date of update: 23-8-2024

Product specifications

Tough PLA is a 3D printer filament that is extremely impact resistant. Tough PLA combines the durability of ABS-like strength properties and is significantly more stiff than ABS filaments.

Impact energy: 875 mJ

Important key features

Superb layer adhesion
Stiff, strong and durable
Compatible with AquaSolve PVA and BVOH for complex multi-extrusion 3D printing

Suitable applications

Tooling and manufacturing aids
Functional prototypes
Snap-fit assemblies

Recommended pretreatment

Drying

Recommended
30 - 40 °C
6 h

Print with

Enclosure Yes
Dry box No

Recommended print settings regular speed

Print speed 25 - 130 mm/s
Nozzle temperature 190 - 230 °C
Bed temperature 50 - 60 °C
Fan speed 80 - 100 %

Recommended print settings high speed

Tough PLA is high speed compatible. Our recommended settings will be added once available. Please take note that the nozzle temperature and fan speed need to be raised when printing at high speed.

Material properties	Typical value	Unit of Measure	Test method	Test condition
Density				
Specific gravity	1,2	g/cm ³	ASTM D792	
Melt flow rate	9,43	g/10min	ASTM D1238	210°C/2,16kg
Mechanical properties				
Impact strenght	2.09	J/cm ²	ISO 79	Charpy notched 23°C
Tensile strenght at yield	53,2	MPa	ASTM D638	
Tensile strenght at break	43,5	MPa	ASTM D638	
Tensile modulus				
Elongation at yield	14,5	%	ASTM D638	
Elongation at break	15	%	ASTM D638	
Flexural strenght				
Flexural modulus	432,8	MPa	ASTM D638	
Rockwell hardness				
Thermal properties				
Melting temperature				
Heat deflection temperature	55	°C	ASTM E2092	HDT A
Vicat softening temperature				
Glass transition temperature	60	°C	ASTM D3418	

Product export information

HS code

39169090

Description

Monofilament for 3D printing

Origin

European Union

Disclaimer

The product- and technical data provided in this datasheet is correct to the best of FormFutura BV's knowledge and are intended for reference and comparison purposes only. Actual values may vary according to printing conditions, model complexity, environmental conditions, etcetera. Typical values are indicative only and are not to be construed as being binding specifications. All other information supplied, including that herein, is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine a product's suitability for a particular purpose. We make no warranty, express or implied, including regarding any information supplied or the data upon which it is based or the results to be obtained from the use of such products or information, or concerning product, whether of satisfactory quality, merchantability, fitness for any particular purpose or otherwise, or with respect to intellectual property infringement as a result of use of information or products, and none shall be implied.

