

	STANDARD	UNIT	TYPICAL VALUE
PHYSICAL PROPERTIES			
Density	ISO 527	g/cc	1.24
MECHANICAL PROPERTIES			
Tensile Strength, Break	ISO 527	MPa	62
Tensile Modulus	ISO 527	MPa	2960
Tensile Elongation, Break	ISO 527	%	12
Flexural Strength	ISO 178	MPa	52
Flexural Modulus	ISO178	MPa	3295
THERMAL PROPERTIES			
Glass Transition Temperature (Tg)	DSC	°C	55
Deflection Temperature at 0.45 MPa (66psi)	ISO 75	°C	60

DATE ISSUED

MONTH
1 2 3 4 5 6 7 **8** 9 10 11 12

DAY
1 2 3 4 5 6 7 8 9 10 **11** 12 13 14 15 16 17
18 19 20 21 22 23 24 25 26 27 28 29 30 31

YEAR
2021 2022 **2023**

DISCLAIMER

The technical data contained on this data sheet should not be used to establish specifications limits or used alone as the basis of design. The data provided is not intended to substitute any testing that may be required to determine fitness for any specific use.